

PRECIPITATED BARIUM SULPHATE

Blanc Fixe Utra is:

The optimal extender for almost all applications in the production of paints ,coatings & plas-tic Chemaically precipitated, pure barium sulfate

Resistant to water, acide ,alkali, & organic solvents

Resistant to light and to industrial waste gases (e.g., sulfaur dioxide)

Having excellent dispersion properties, a very high gloss and low binder demand.

Also having extremely low chloride content along with a greatly reduced electric conductivity

DESCRIPTION

Туре	Technical Oxide White Powder	
Delivery form		
Molecular Weight	233	
Chemical Formula	BaSO4	
EINECS	231-784-4	
CAS-No.	7727-43-7	
REACH No.	Under Process	

TYPICAL ANALYSIS

Parameter	unit	Testing Method	Specification
BaSO4 Content	(Wt%)	DIN EN ISO 3262-3	<u>></u> 98.0
Average Particle Size D ₅₀	(um)	laser Diffraction Malven (Wet)	≤ 1.0
Degree of Lightness	(L*)	Spectrophotometer	≥ 98.0
Oil Absorption index	(g/100g)	ASTMD 1483	13 +/. 1
pH Value			8 +/. 1
Electrical Conductivity	(uS/cm)		≤ 200
Solubility in Water	(Wt%)	₽	0.5
Sieve Residue > 45 um	(Wt%)		0.05
Volatile Fraction	(Wt%)		0.05
Density	(g/mL)	¥	1.00

PACKAGING	25 Kg Paper Bags	
	25 Kg HDPE Bags	35
	1000 Kg Bulk HDPE Bags	



"WE THE SUPERIOR"

♥ 1/707-4, Dwaraka Nagar, Yerramukkapalli, YSR District, (Cuddapah) Kadapa-516004.

🔀 info@eliteminerals.in 🔀 elitemineralsind@gmail.com 🌐 www.eliteminerals.in

Factory: 1107/9,10,34&35, Bommavaram, Obulavaripalli, Rly. Kodur, Kadapa - 516 101. INDIA. Chennai Office: 16/41 P.P. Road, Balaji Nagar, Chennai - 600 014. Tamil Nadu. INDIA.